



CENTRICO

Seamless Stainless Steel Tubing



Element	Composition, wt. %
Carbon	0.035 max
Silicon	1.00 max
Manganese	2.00 max
Phosphorus	0.045 max
Sulphur	0.03 max
Nickel	10.0 to 14.0
Chromium	16.0 to 18.0
Molybdenum	2.00 to 3.00

Seamless stainless steel tube
 ASTM A269 / A213(A.W.)
 TP316/316L cold drawn
 Hardness RB 80 maximum
 Certificate to EN-10204-3.1

Tubing OD	Wall Thickness	Part Number	Length	Weight	Allowable Working Pressure
inches	inches		m	kg	psi
1/4	0.035	T-316L-0250-0035	6.0	0.73	5200
	0.049	T-316L-0250-0049		0.95	7600
	0.065	T-316L-0250-0065		1.16	10300
3/8	0.035	T-316L-0375-0035		1.16	3350
	0.049	T-316L-0375-0049		1.55	4850
	0.065	T-316L-0375-0065		1.96	6550
1/2	0.035	T-316L-0500-0035		1.58	2650
	0.049	T-316L-0500-0049		2.14	3750
	0.065	T-316L-0500-0065		2.74	5150
	0.083	T-316L-0500-0083		3.36	6750
3/4	0.049	T-316L-0750-0049		3.32	2450
	0.065	T-316L-0750-0065		4.32	3350
	0.083	T-316L-0750-0083		5.38	4250
1	0.049	T-316L-1000-0049		4.52	1800
	0.065	T-316L-1000-0065		5.90	2400
	0.083	T-316L-1000-0083	7.37	3100	

CENTRICO

Seamless Stainless Steel Tubing